



Charcoal is a medium density, tight grain limestone with soft grey hues that make it highly versatile in design possibilities. It is available in all architectural and flatwork formats, as well as interior and exterior veneer.

SOURCE: Texas Limestone

Applications

Chopped  
Thin Veneer  
Tile

Mosaics  
Moldings  
Architectural Elements

Considerations



Freeze Thaw



Medium Traffic



Low Variation

Technical Data

ASTM 97 Density	ASTM 97 Absorption	ASTM C170 Compressive Strength	ASTM C880 Flexural Strength	ASTM 353 Abrasion Resistance
142.6 lbs/ft <sup>3</sup>	4.91%	4650 lbs/in <sup>2</sup>	920 lbs/ft <sup>2</sup>	low

Care and Maintenance:

- High acid sensitivity is a property of limestone. Care must be taken in the presence of acidic foods and cleaning products.
- Low abrasion resistance is inherent in most limestones. Light scratching will occur with exposure to abrasives. A patina will result over time. It is recommended to use mats at entrances in flooring applications.
- This limestone has a low to moderate absorption rate. It is recommended to seal this material prior to use. Sealers allow for additional time to “clean up” the spill, before it has time to result in a stain